

ALCOM® PP 620/2 SV1246-04MCO

Polypropylene Homopolymer

ALBIS PLASTIC GmbH

Message:

ALCOM® PP 620/2 SV1246-04MCO is a Polypropylene Homopolymer (PP Homopolymer) product. It is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PP 620/2 SV1246-04MCO include household applications and housings.

Characteristics include:

REACH Compliant

RoHS Compliant

High Flow

Homopolymer

General Information			
Features	High Flow		
	Homopolymer		
Uses	Household Goods		
	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Metallized - Colors		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	66.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1500	MPa	ISO 527-2
Tensile Strain (Break)	22	%	ISO 527-2
Flexural Modulus	1550	MPa	ISO 178
Flexural Stress	43.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	51	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	66.0	°C	ISO 75-2/A
Vicat Softening Temperature	97.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	80.0 to 100	°C	
Desiccant Dryer	80.0 to 100	°C	
Drying Time			

Circulation Dryer	2.0 to 4.0	hr
Desiccant Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	200 to 270	°C
Mold Temperature	20.0 to 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

