MARPOL® Homo 35.NA

Polypropylene Homopolymer

Marco Polo International, Inc.

Message:

Additives: Nucleation and Antistat

Recommended Applications: Large thin wall parts, caps, and closures. Homo 35.NA complies with all applicable FDA regulations for food contact.

| General Information | | | |
|---|--------------------------------------|----------|-------------|
| Additive | Antistatic | | |
| | Nucleating Agent | | |
| Features | Antistatic | | |
| | Food Contact Acceptable | | |
| | Homopolymer | | |
| | Nucleated | | |
| Uses | Caps | | |
| | Closures | | |
| | Thin-walled Parts | | |
| Agency Ratings | FDA Food Contact, Unspecified Rating | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.905 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 35 | g/10 min | ASTM D1238 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (R-Scale) | 107 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 1720 | MPa | ASTM D638 |
| Tensile Strength (Yield) | 38.6 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 11 | % | ASTM D638 |
| Flexural Modulus | 1790 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 43 | J/m | ASTM D256A |
| Unnotched Izod Impact (23°C) | 850 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa, Unannealed) | 127 | °C | ASTM D648 |
| Melting Temperature | 166 | °C | DSC |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

