

# NaturePlast NP DU 202

Polyamide 1010

NaturePlast

Message:

The R&D progress allows today to produce some of the conventional polymers partially or totally from vegetable resources and no longer from fossil resources.

BioPA grades commercialized by NaturePlast have the same properties as the conventional PA and can be transformed on plastic processing standard equipments.

Markets: automotive, technical parts, packaging, textiles, etc.

Properties

Properties similar to oil based PA.

Processing easiness.

Recyclable in existing PA streams.

General Information			
Features	Good Processability		
	Recyclable Material		
	Renewable Resource Content		
Uses	Automotive Applications		
	Engineering Parts		
	Packaging		
	Textile Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm <sup>3</sup>	ISO 1183
Viscosity Number	160	cm <sup>3</sup> /g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ISO 527-2
Tensile Strain (Break)	> 50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	171	°C	ISO 306/B
Additional Information	Nominal Value	Unit	Test Method
Biobased Content	100	%	ASTM D6866

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

