

RELENE® LL36RA045UV

Linear Low Density Polyethylene

Reliance Industries Limited

Message:

LL36RA045UV is a Butene Comonomer based Linear Medium Density Polyethylene (LLDPE). This grade is stabilised with appropriate quantity of HALS to give a long service with continuous outdoor exposure with or without blending of any carbon black. LL36RA045UV when pulverised into 20-30 mesh powder offers good processability. This grade has very good Environmental Stress Crack Resistance (ESCR) and a combination of hardness and impact strength. This grade contains normal dose of AO and high dose of UV stabiliser.

General Information			
Additive	Antioxidant UV Stabilizer		
Features	Antioxidant Butene Comonomer Food Contact Acceptable Good Impact Resistance High ESCR (Stress Crack Resist.) High Hardness		
Agency Ratings	FDA 21 CFR 177.1520 IS 10141-1982 IS 10146-1982		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.936	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (10% Igepal, F50)	> 350	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 2.00 mm, Compression Molded)	17.7	MPa	ASTM D638
Tensile Elongation (Yield)	20	%	ASTM D638
Flexural Modulus (3.20 mm, Compression Molded)	588	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm, Injection Molded)	55	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

