

Anjacom® 455-GF10

Polybutylene Terephthalate
Almaak International GmbH

Message:

Anjacom® 455-GF10 is a Polybutylene Terephthalate (PBT) material filled with 10% glass fiber. It is available in Europe. Primary attribute of Anjacom® 455-GF10: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.38	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	25.0	cm³/10min	ISO 1133
Water Absorption			ISO 62
23°C, 24 hr	0.40	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4500	MPa	ISO 527-2/1
Tensile Stress (Break)	85.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.8	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.2	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	23	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	205	°C	ISO 75-2/B
1.8 MPa, Unannealed	185	°C	ISO 75-2/A
Vicat Softening Temperature	202	°C	ISO 306/B50
Melting Temperature	224	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	4.0 to 10	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	80.0 to 110	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT