

LubriOne™ NL-30CF/15T Black

Polyamide 612
PolyOne Corporation

Message:

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General Information			
Features	Electrically Conductive		
	Good Wear Resistance		
	High Stiffness		
	Lubricated		
Uses	Appliance Components		
	Automotive Applications		
	Bearings		
	Business Equipment		
	Consumer Applications		
	Conveyor Parts		
	Gears		
	Industrial Applications		
	Printer Parts		
	Pulleys		
	Rollers		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.20 to 1.0	%	
Across Flow	1.0 to 2.0	%	
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	19300	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	169	MPa	
Break ²	169	MPa	

Tensile Elongation ³ (Break)	2.9	%	ASTM D638
Flexural Modulus	14500	MPa	ASTM D790
Flexural Strength	269	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.14		
vs. Steel - Static	0.26		
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm, Injection Molded)	100	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	212	°C	
1.8 MPa, Unannealed, 3.18 mm	198	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+3	ohms	ASTM D257
Volume Resistivity	1.0E+2 to 1.0E+3	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	243 to 271	°C	
Mold Temperature	82.2 to 93.3	°C	
NOTE			
1.	Type I, 5.1 mm/min		
2.	Type I, 5.1 mm/min		
3.	Type I, 5.1 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT