

SUPRAN® LFT PA A1340

Polyamide 66

SAMBARK

Message:

40% long glass fiber reinforced polyamide 66. High Stiffness, superior mechanical balanced & heat stable.

General Information			
Filler / Reinforcement	Long Glass Fiber,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	High Stiffness		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D648
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	206	MPa	ASTM D638
Tensile Elongation (Break)	2.9	%	ASTM D638
Flexural Modulus	11100	MPa	ASTM D790
Flexural Strength	255	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	230	J/m	
23°C	220	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	255	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	280 to 305	°C	
Mold Temperature	70.0 to 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

