

# ELASTOSIL® RT 685 A/B

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, RTV-2

Coatings, Paints & Coatings

General Information			
Uses	Coating Applications		
	Screen Printing		
Processing Method	Coating		
	Encapsulating		
	Potting		
Uncured Properties	Nominal Value	Unit	Test Method
Color	White		
Viscosity	40	Pa · s	ISO 3219
Pot Life	2900	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	40		ISO 868
Tensile Strength	4.00	MPa	ISO 37
Tensile Elongation at Break	250	%	ISO 37
Compression Set	10	%	DIN ISO 815-B
Tear Strength	5.00	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

