

Ravaflex EPDM P

Ethylene Propylene Diene Terpolymer

Ravago Group

Message:

Reprocessed free-flowing terpolymer of ethylene, propylene and ENB with a very good processibility.

| General Information | |
|---------------------|-------------------|
| Features | Antioxidation |
| | Workability, good |
| | Terpolymer |
| Appearance | White |
| | White-like |

| Physical | Nominal Value | Unit | Test Method |
|-------------------------------------|---------------|-------------------|-----------------|
| Density | 0.875 - 0.885 | g/cm ³ | ASTM D1505 |
| Mooney Viscosity (ML 1+4, 121°C) | 15 - 35 | MU | ASTM D1646 |
| Ethylene Content | 67.0 - 77.0 | wt% | ASTM D3900 |
| Ethylidene Norbornene (ENB) Content | 1.0 - 3.0 | wt% | ASTM D6047 |
| Antioxidant Additive | Nonstaining | | |
| Moisture Content (105°C) | | % | Internal method |
| Ash content-1 hr (550°C) | | % | ASTM D297 |
| Packaging | 1200 | g | |
| Additional Information | Nominal Value | Unit | |

It shows an excellent resistance to oxidative and ozone degradation. It is used in bitumen and in plastics modification. It can be used in wire and cable applications.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT