

PC-COM™ PC422-50

Polycarbonate
Polymer Compounders Limited

Message:
PC-COM PC422-50 is a high flow general purpose polycarbonate grade with UV absorption. Applications include automotive interior covers and lighting.

General Information			
Additive	UV Stabilizer		
Features	General Purpose		
	Good UV Resistance		
	High Flow		
Uses	Automotive Interior Parts		
	General Purpose		
	Lighting Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	22	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Water Absorption			ISO 62
Saturation, 23°C	0.15	%	
Equilibrium, 23°C, 50% RH	0.35	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2350	MPa	ISO 527-2/1
Tensile Stress (Yield)	63.0	MPa	ISO 527-2/50
Tensile Strain			
Yield	6.0	%	ISO 527-2/50
Break	120	%	ISO 527-2
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Notched Izod Impact Strength (23°C)	8.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	136	°C	ISO 75-2/Be
1.8 MPa, Unannealed	124	°C	ISO 75-2/Ae

Vicat Softening Temperature	144	°C	ISO 306/B50
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.50 mm	V-2		
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	280	°C	
Mold Temperature	90.0	°C	
Injection Velocity	60	mm/sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

