

Grilon® TSGL-50/4 black 9833

Polyamide 66/6 Copolymer

EMS-GRIVORY

Message:

Grilon® TSGL-50/4 black 9833 is a Polyamide 66/6 Copolymer (Nylon 66/6) material filled with 50% long glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding. Primary attribute of Grilon® TSGL-50/4 black 9833: Flame Rated.

Typical applications include:

- Automotive
- Electrical/Electronic Applications
- Appliances
- Consumer Goods
- Engineering/Industrial Parts

General Information				
UL YellowCard		E53898-100126204		
Filler / Reinforcement		Long Glass Fiber,50% Filler by Weight		
Uses		Appliance Components		
		Automotive Applications		
		Automotive Exterior Parts		
		Automotive Interior Parts		
		Connectors		
		Consumer Applications		
		Electrical/Electronic Applications		
		Engineering Parts		
		Household Goods		
		Hydraulic Applications		
		Industrial Applications		
		Pneumatic Applications		
		Power/Other Tools		
		Sporting Goods		
Forms		Granules		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.55	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.30	--	%	
Flow	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	4.5	--	%	
Equilibrium, 23°C, 50% RH	1.5	--	%	
Hardness	Dry	Conditioned	Unit	Test Method

Ball Indentation Hardness	315	205	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	17800	12800	MPa	ISO 527-2
Tensile Stress (Break)	255	180	MPa	ISO 527-2
Tensile Strain (Break)	2.0	2.3	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	35	40	kJ/m²	
23°C	35	40	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	85	80	kJ/m²	
23°C	95	100	kJ/m²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	255	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	235	--	°C	ISO 75-2/C
Continuous Use Temperature				Internal Method
-- ¹	120 to 130	--	°C	
-- ²	220	--	°C	
Melting Temperature ³	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.0E-5	--	cm/cm/°C	
Transverse	5.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+12	ohms·cm	IEC 60093
Electric Strength	27	22	kV/mm	IEC 60243-1
Comparative Tracking Index	--	500	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA66+PA6, MH, 14-190N, GF50-			ISO 1874
NOTE				
1.	Long Term			
2.	Short Term			
3.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

