

Mytex® AS33K-02

Compounded Polypropylene

Mytex Polymers

Message:

Talc Filled compounded polypropylene produced for automotive interior applications using Mytex® Technology.

| General Information | | | |
|---|---------------------------|-------------------|-------------|
| Filler / Reinforcement | Talc,20% Filler by Weight | | |
| Uses | Automotive Applications | | |
| | Automotive Interior Parts | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.04 | g/cm ³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 24 | g/10 min | ASTM D1238 |
| Ash Content | 20 | % | ASTM D5630 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

