

# SABIC® PP 570P

Polypropylene Homopolymer

SABIC Americas, Inc.

## Message:

PP Homopolymer for Injection Molding

PP 570P is specially developed for producing rigid injection molding articles for general purpose applications. It gives consistent processability, good mechanicals and high gloss in the products.

Typical Applications

PP 570P can be used mainly for various houseware articles.

General Information			
Features	Food Contact Acceptable		
	Good Processability		
	High Gloss		
	High Rigidity		
	Homopolymer		
Uses	General Purpose		
	Household Goods		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity <sup>1</sup>	0.905	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.2 to 2.5	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Injection Molded)	32.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	11	%	ASTM D638
Flexural Modulus - 1% Secant (Injection Molded)	1630	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	35	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	100	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525 <sup>2</sup>

Injection	Nominal Value	Unit
Rear Temperature	200 to 240	°C
Middle Temperature	200 to 240	°C
Front Temperature	200 to 240	°C
Mold Temperature	15.0 to 40.0	°C

#### NOTE

1. 23°C
2. Rate B (120°C/h)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

