

Geon™ HTX M6307

Polyvinyl Chloride Alloy

PolyOne Corporation

Message:

Geon™ HTX M6307 is a Polyvinyl Chloride Alloy (PVC Alloy) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ HTX M6307 include outdoor applications, construction applications, electrical/electronic applications and wire & cable.

Characteristics include:

Flame Rated

High Flow

Impact Resistant

General Information			
UL YellowCard	E41877-234302	E41877-234303	
Features	High Flow		
	Low Temperature Impact Resistance		
Uses	Construction Applications		
	Electrical/Electronic Applications		
	Outdoor Applications		
	Telecommunications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Spiral Flow	76.2	cm	
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Outdoor Suitability (Gray)	f1		UL 746C
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	1720	MPa	ASTM D638
Tensile Strength ² (Yield)	29.6	MPa	ASTM D638
Tensile Elongation ³ (Break)	94	%	ASTM D638
Flexural Modulus	1790	MPa	ASTM D790
Flexural Strength	50.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256A
-40°C, 3.18 mm, Injection Molded	160	J/m	
-18°C, 3.18 mm, Injection Molded	370	J/m	
0°C, 3.18 mm, Injection Molded	590	J/m	
23°C, 3.18 mm, Injection Molded	750	J/m	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	73.9	°C	
0.45 MPa, Annealed, 6.35 mm	81.1	°C	
1.8 MPa, Unannealed, 6.35 mm	68.9	°C	
1.8 MPa, Annealed, 6.35 mm	73.9	°C	
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
Flammability	Nominal Value	Test Method	
	V-0		

Flame Rating (2.01 mm, ALL)	5VA	UL 94	
Additional Information	Nominal Value	Unit	
QUV Weatherometer ⁴	0.58	%	
Injection	Nominal Value	Unit	
Drying Temperature	68.3	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	202 to 207	°C	

NOTE		
1.	Type I, 51 mm/min	
2.	Type I, 51 mm/min	
3.	Type I, 51 mm/min	
4.	351 Lamp, All Colors, detla E (CIE), 24 hrs light, 300 hrs, No Moisutre	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

