# Kingfa FRHIPS-960PC

## High Impact Polystyrene

## Kingfa

#### Message:

Kingfa FRHIPS-960PC is a High Impact Polystyrene material. It is available in Asia Pacific or North America. Important attributes of Kingfa FRHIPS-960PC are:

Flame Rated

Flame Retardant

Impact Resistant

Rigid

**UV** Stabilized

Typical applications include:

Housings

**Printing Applications** 

General Information			
UL YellowCard	E171666-225774		
Additive	UV Stabilizer		
Features	Flame Retardant		
	High Impact Resistance		
	High Rigidity		
Uses	Housings		
	Printer		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	92		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (23°C, Injection Molded)	21.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break, 23°C, Injection Molded)	35	%	ASTM D638
Flexural Modulus <sup>3</sup> (23°C, Injection Molded)	2000	MPa	ASTM D790
Flexural Strength <sup>4</sup> (23°C, Injection Molded)	35.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	94	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1	1.8				
MPa, Unannealed, 6.40 mm)	75.0	°C	ASTM D648		
Vicat Softening Temperature	92.0	°C	ASTM D1525 <sup>5</sup>		
Electrical	Nominal Value	Unit	Test Method		
Surface Resistivity	1.0E+16	ohms	ASTM D257		
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257		
Flammability	Nominal Value	Unit	Test Method		
Flame Rating (3.00 mm)	V-0		UL 94		
NOTE					
1.	50 mm/min	50 mm/min			
2.	50 mm/min	50 mm/min			
3.	2.0 mm/min	2.0 mm/min			
4.	2.0 mm/min	2.0 mm/min			
5.	Rate B (120°C/h), Loading	Rate B (120°C/h), Loading 1 (10 N)			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

