

BIOH™ Polyol X-0210

Biodegradable Polymers

Cargill Industrial Bio-Products

Message:

Bio-based polyol for use in polyurethanes.

General Information			
Features	Biodegradable		
	Renewable Resource Content		
Uses	Foam		
Processing Method	Foam Processing		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ASTM D1298
Acid Number ¹	1.70	mg KOH/g	Internal Method
Gardner Color ²	< 2.00		Internal Method
Molecular Weight ³	1100		Internal Method
Water Content	3000	ppm	ASTM E1064-04A
Flash Point	> 130	°C	ASTM D93
Functionality - Calculated	4.40		
Hydroxyl Value ⁴	235	mg KOH/g	ASTM E1899-97
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity ⁵ (25°C)	8900	cP	ASTM D2196
NOTE			
1.	AOCS CD 3d-63		
2.	AOCS Td Ia-64		
3.	Vapor Phase Osmometry		
4.	Hydroxyl Type: 100% secondary, Known Structure		
5.	(8B)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT