3M[™] Dyneon[™] PTFE Compound TF 8465

Polytetrafluoroethylene

3M Advanced Materials Division

Message:

3M™ Dyneon™ PTFE Compound TF 8465 is a free-flowing suspension PTFE compound containing 25% glass fibre for compression and automatic moulding. Special Features Increased thermal dimensional stability Increased surface hardness Improved deformation under load Reduced friction & wear Good chemical stability High limiting oxygen index (LOI) Low friction behaviour Very good mechanical properties Exceptional temperature resistance

General Information		
Filler / Reinforcement	Glass fiber reinforced material, 25% filler by weight	
Features	Low friction coefficient	
Uses	Seals	
	Application in Automobile Field	

Forms	Powder		
Processing Method	Compression molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.17	g/cm³	ASTM D4745-06
Apparent Density	0.78	g/cm³	ASTM D4894-07
Molding Shrinkage - Flow	0.90	%	ASTM D4894-07
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		DIN 53505
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	15.5	MPa	ASTM D4745-06
Tensile Elongation (Break)	260	%	ASTM D4745-06

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

