

Badadur® PBT8

Polybutylene Terephthalate

Bada AG

Message:

Medium viscosity, standard injection moulding grade with good mechanical properties

General Information			
Features	Medium Viscosity		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Water Absorption			ISO 62
Saturation, 23°C	0.50	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (23°C)	2650	MPa	ISO 527-2/1
Tensile Stress ² (Yield, 23°C)	57.0	MPa	ISO 527-2/50
Tensile Strain ³ (Yield, 23°C)	4.0	%	ISO 527-2/50
Nominal Tensile Strain at Break ⁴ (23°C)	> 50	%	ISO 527-2/50
Flexural Stress ⁵ (23°C)	85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶			ISO 179/1eA
-30°C	4.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Charpy Unnotched Impact Strength ⁷			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength ⁸			ISO 180/1A
-30°C	4.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁹			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	60.0	°C	ISO 75-2/A
Melting Temperature (DSC) ¹⁰	223	°C	ISO 3146
CLTE ¹¹			DIN 53752
Flow : 4.00 mm	1.4E-4	cm/cm/°C	
Transverse : 4.00 mm	1.4E-4	cm/cm/°C	
Maximum Service Temperature			

20000 hrs	120	°C	
some hours	160	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ¹²	> 1.0E+14	ohms	IEC 60093
Volume Resistivity ¹³	> 1.0E+16	ohms·cm	IEC 60093
Electric Strength ¹⁴	24	kV/mm	IEC 60243-1
Relative Permittivity ¹⁵ (1 MHz)	3.20		IEC 60250
Dissipation Factor ¹⁶ (1 MHz)	0.018		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm ¹⁷	HB		
1.60 mm ¹⁸	HB		
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	60.0 to 100	°C	
NOTE			
1.	Test Specimen accordng to ISO 3167, Type A		
2.	Test Specimen accordng to ISO 3167, Type A		
3.	Test Specimen accordng to ISO 3167, Type A		
4.	Test Specimen accordng to ISO 3167, Type A		
5.	80x10x4 mm		
6.	80x10x4 mm		
7.	80 x 10 x 4 mm		
8.	80x10x4 mm		
9.	110x10x4mm		
10.	10 K/min, compound for moulding		
11.	>=10x10x4 mm		
12.	80x80x1 mm		
13.	80x80x1 mm		
14.	80x80x1 mm		
15.	80x80x1 mm		
16.	80x80x1 mm		
17.	125x13x.8 mm		
18.	125x13x1.6 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT