Taitacell EPS-391ML

Expanded Polystyrene

Taita Chemical Company, Ltd.

Message:

Taitacell EPS-391ML is a kind of expanded polystyrene material. This product is available in North America or Asia Pacific region. The processing method is foam processing. The main characteristics of Taitacell EPS-391ML are: rapid prototyping cycle. the typical application field of Taitacell EPS-391ML is: packaging

| General Information | | | |
|-----------------------------------|--------------------|-------|-------------|
| Features | Fast molding cycle | | |
| | Good stability | | |
| | Steam resistance | | |
| | | | |
| Uses | Media packaging | | |
| | Food packaging | | |
| | | | |
| Forms | Particle | | |
| Processing Method | Foam treatment | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.0185 | g/cm³ | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Strength | 0.196 | MPa | ASTM D790 |
| Compressive Strength (10% Strain) | 0.0686 | MPa | ASTM D695 |
| Additional Information | | | |

Density was tested in accordance with the JIS K-7222 standard.Compressive strength was tested in accordance with the JIS K-7220 standard.Flexural strength was tested in accordance with the JIK A-9551 standard.Chemical Resistance of Alkali: GoodChemical Resistance of Org. Solvent: PoorDensity, JIS K-7222: 12 to 25g/IThermal Conductivity, JIK A-9551: 0.028Kcal/mh cChemical Resistance of Acid, No standard: Good

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

