

Sumikon® PM-6630 (Type: J Black)

Phenolic

SBHPP

Message:

SUMIKON PM-6630 Type J Black is a Short Glass fiber & Mineral molding compound based on Phenolic Novolac polymer. It is supplied in the form of Granular/Molding Powder for Molding. This grade is official registered UL with V-0 (t=3.0).

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
	Mineral filler		
	Inorganic filler		
Appearance	Black		
Forms	Powder		
	Particles		
Processing Method	Resin transfer molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.79	g/cm ³	JIS K6911
Molding Shrinkage - Flow	0.20	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	15600	MPa	JIS K6911
Flexural Strength	207	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.3	kJ/m ²	JIS K6911
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	216	°C	JIS K6911
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	10	kV/mm	JIS K6911
Insulation Resistance ²	5.0E+11	ohms	JIS K6911
NOTE			
1.	Method B (step by step)		
2.	As molded		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

