

ELASTOSIL® R 401/60 KX

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV

Ignition and Battery Cables, Cable Industry

Extrudates, Technical, Plastics and Rubber Processing

Extrudates, food contact, Plastics and Rubber Processing

Extrudates, Automotive, Automotive & Transportation

Sealant Profiles, Construction

General Information			
Features	Food Contact Acceptable		
	General Purpose		
Uses	Automotive Applications		
	Compounding		
	Profiles		
	Wire & Cable Applications		
Processing Method	Calendering		
	Extrusion		
	Profile Extrusion		
	Wire & Cable Extrusion		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.18	g/cm ³	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	59		DIN 53505
Tensile Strength	11.0	MPa	DIN 53504
Tensile Elongation at Break	460	%	DIN 53504
Tear Strength	25.0	kN/m	ASTM D624B
Rebound Resilience	51	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

