

Titalon® 2250AF

Polyamide 66

Titan Plastics Compounds Co., Ltd.

Message:

Titalon®2250AF is a polyamide 66 (nylon 66) material, which contains glass fiber reinforcement and aramid fiber. This product is available in the Asia-Pacific region.

Titalon®The main features of 2250AF are:

flame retardant/rated flame

Wear-resistant

Lubrication

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
	Aramid fiber		
Additive	PTFE lubricant		
Features	Good wear resistance		
	Lubrication		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Molding Shrinkage ¹ (3.00 mm)	0.40 - 1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	120	MPa	ISO 527-2
Tensile Strain (Break)	> 4.0	%	ISO 527-2
Flexural Modulus	4200	MPa	ISO 178
Flexural Stress	180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	240	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	260 - 290	°C	

Mold Temperature	60.0 - 100	°C
Injection instructions		
Injection Pressure: 30 to 70%Injection Velocity: 30 to 60%		
NOTE		
1.	50x70x3 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

