

POCAN® B 3217 XF 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 16 % glass fibers, injection molding, improved flowability, improved impact strength

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 16% filler by weight		
Features	Impact resistance, good		
	Good liquidity		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.40	g/cm ³	ISO 1183
Apparent Density	0.70	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	35.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction: 260°C, 2.00mm ¹	1.1	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.10	%	ISO 294-4
Flow direction: 260°C, 2.00mm ³	0.60	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.10	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	6000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	105	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.2	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	5800	MPa	ISO 178/A
Flexural Stress ⁶			
3.5% strain	165	MPa	ISO 178/A
23°C	170	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	%	
ISO Shortname	PBT, GHMR, 07-060, GF16		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	35	kJ/m ²	ISO 179/1eU

23°C	45	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	30	kJ/m ²	ISO 180/1U
23°C	40	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	200	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B120
Melting Temperature ⁸	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	4.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.3E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	350	V	IEC 60112
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
Processing (Melt) Temp	250 - 270	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	60x60x2; MT 80°C; 600 Bar		
2.	60x60x2		
3.	60x60x2; MT 80°C; 600 Bar		
4.	60x60x2		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	Pull Rate: 2 mm/min; 50% RH		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT