

Medalist® MD-50148

Thermoplastic Elastomer

Teknor Apex Company

Message:

Medalist™MD-50148 is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is extrusion or injection molding.

Typical application areas include:

medical/health care

safety equipment

General Information	
Uses	Safety equipment Drug Medical/nursing supplies
Appearance	Clear/transparent
Forms	Particle
Processing Method	Extrusion Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.878	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	75	g/10 min	ASTM D1238

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A, 1 sec	62		ASTM D2240
Shaw A, 5 seconds	55		ASTM D2240
Shaw A, 15 seconds	53		ASTM D2240

Elastomers	Nominal Value	Unit	Test Method
Tensile Strength - Flow (Break)	6.27	MPa	ASTM D412
Tensile Elongation - Flow (Break)	680	%	ASTM D412

Injection	Nominal Value	Unit
Rear Temperature	127 - 149	°C
Middle Temperature	138 - 160	°C
Front Temperature	149 - 171	°C
Nozzle Temperature	171 - 193	°C
Processing (Melt) Temp	171 - 193	°C
Mold Temperature	21.1 - 37.8	°C
Injection Pressure	1.38 - 5.52	MPa
Back Pressure	0.172 - 0.689	MPa
Screw Speed	50 - 100	rpm

Cushion	3.81 - 25.4	mm
---------	-------------	----

Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	138 - 149	°C
Cylinder Zone 2 Temp.	149 - 160	°C
Cylinder Zone 3 Temp.	160 - 182	°C
Cylinder Zone 5 Temp.	171 - 193	°C
Die Temperature	182 - 204	°C

Extrusion instructions

Screw Speed: 30 to 100 rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

