

# Bynel® 3126

Ethylene Vinyl Acetate Copolymer  
DuPont Packaging & Industrial Polymers

Message:

BYNEL® Series 3100 resins are acid/acrylate-modified ethylene vinyl acetate polymers. They are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.

BYNEL 3100 series resins adhere to a wide variety of materials. They are most often used to adhere to PE, ionomers, EVA, and in some cases PVC, PS, HIPS, and PP.

General Information	
Features	Good adhesion
Uses	Adhesive
Agency Ratings	FDA 21 CFR 177.1350
Forms	Particle
Processing Method	Co-extrusion molding Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.926	g/cm <sup>3</sup>	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.1	g/10 min	ASTM D1238, ISO 1133

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	60.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	87.0	°C	ASTM D3418, ISO 3146
Freezing Point	67	°C	ASTM D3418

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	110	°C
Cylinder Zone 2 Temp.	135	°C
Cylinder Zone 3 Temp.	160	°C
Cylinder Zone 4 Temp.	185	°C
Cylinder Zone 5 Temp.	185	°C
Adapter Temperature	185	°C
Melt Temperature	< 235	°C
Die Temperature	185	°C

Extrusion instructions
Processing conditions shown are for blown film.Processing conditions for cast film/sheet:Zone 1: 135°CZone 2: 160°CZone 3: 185°CZone 4: 210°CZone 5: 235°CAdapter: 235°CDie: 235°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

