

# Ravamid® R200 GF 10

Polyamide 6

Ravago Group

Message:

10% glass fibre reinforced PA6 compound for injection moulding

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm <sup>3</sup>	ISO 2781
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5200	MPa	ISO 527-2
Tensile Stress (Yield)	100	MPa	ISO 527-2
Tensile Strain (Break)	3.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	6.0	kJ/m <sup>2</sup>	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	210	°C	ISO 75-2/B
1.8 MPa, Unannealed	195	°C	ISO 75-2/A
Vicat Softening Temperature	206	°C	ISO 306/A120
Melting Temperature	220 to 225	°C	
Flammability	Nominal Value		Test Method
Flame Rating <sup>1</sup> (1.60 mm)	HB		Internal Method
NOTE			

1. UL94 internally tested

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

**Susheng Import & Export Trading Co.,Ltd.**

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

