

Latiohm 66-08 PD02 G/35

Polyamide 66

LATI S.p.A.

Message:

Dissipative compound based on Polyamide 66 (PA 66).
Glass fibres.

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.75 to 1.1	%	
Flow : 2.00 mm	0.40 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	7900	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	90.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	55	kJ/m²	ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	65	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	250	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	°C	ISO 75-2/A
Vicat Softening Temperature	230	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8	ohms	ASTM D257
Volume Resistivity	6.0E+8	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	275 to 300	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate		
NOTE			

1. at 60 Mpa of cavity pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT