

HANWHA EVA 1157

Ethylene Vinyl Acetate Copolymer
Hanwha Chemical

Message:

HANWHA EVA 1157 is manufactured by autoclave high pressure process and designed for variety of extrusion coating application such as thermal film(Laminex film) and flexible film etc.. EVA 1157 is well known for its excellent processability and high quality assurance.

General Information			
Features	Good Adhesion		
	Good Drawdown		
	Good Processability		
	Low Temperature Heat Sealability		
	Opticals		
Uses	Coating Applications		
	Film		
Forms	Pellets		
Processing Method	Extrusion Coating		
Physical	Nominal Value	Unit	Test Method
Density	0.939	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	16	g/10 min	ASTM D1238
Vinyl Acetate Content	18.0	wt%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	13.5	MPa	ASTM D638
Tensile Elongation (Break)	860	%	ASTM D638
Films	Nominal Value	Unit	Test Method
Seal Initiation Temperature	80.0	°C	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	61.0	°C	ASTM D1525
Peak Melting Temperature	85.0	°C	ASTM D3417
Additional Information	Nominal Value	Unit	
Allowable Coating Speed ¹ (250°C)	> 5.0	m/sec	
Neck-in ² (250°C)	75.0	mm	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	160 to 250	°C	
Cylinder Zone 3 Temp.	160 to 250	°C	
Cylinder Zone 5 Temp.	160 to 250	°C	
Adapter Temperature	250	°C	

Die Temperature	250	°C
NOTE		
1.	100 m/min line speed, 80 kg/hr output	
2.	100 m/min line speed, 80 kg/hr output	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

