

NaturePlast PHI 001

Polyhydroxyalkanoate

NaturePlast

Message:

PHA-type polymers (Polyhydroxyalkanoates) are thermoplastic resins made from renewable vegetal resources, produced by bacterial sugar fermentation. PHA can be processed on standard equipments.
PHA materials are biodegradable and compostable in agreement with standards in use.
Markets : food packaging, horticulture, technical parts...
Properties
Thermal resistance, flexibility and barrier properties higher than PLA. Opaque material.
Some of PHAs are quickly biodegradable.
Additived

General Information			
Additive	Unspecified Additive		
Features	Barrier Resin		
	Biodegradable		
	Compostable		
	Good Flexibility		
	Renewable Resource Content		
Uses	Engineering Parts		
	Food Packaging		
	Lawn and Garden Equipment		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	860	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	45	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	45.0	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

