

VALOX™ 325FC resin

Polybutylene Terephthalate
SABIC Innovative Plastics Europe

Message:

Commercial, VALOX 325FC is compliant with food contact regulations. VALOX 325FC is a general purpose, unreinforced PBT injection moulding resin which contains internal mold release. This new 325FC grade is a good processable resin that exhibits faster and more economical cycle times.

General Information			
Additive	demoulding		
Features	Workability, good		
	Fast molding cycle		
	Compliance of Food Exposure		
	General		
	Good demoulding performance		
Uses	General		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792, ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
250°C/2.16 kg	20.0	cm ³ /10min	ISO 1133
250°C/5.0 kg	50.0	cm ³ /10min	ISO 1133
Molding Shrinkage ¹			Internal method
Flow	2.0 - 2.6	%	Internal method
Transverse flow	0.90 - 1.8	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.34	%	ISO 62
Equilibrium, 23°C, 50% RH	0.080	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ISO 2039-2
Ball Indentation Hardness (H 358/30)	145	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	2500	MPa	ASTM D638
--	2550	MPa	ISO 527-2/1
Tensile Strength			
Yield ³	60.0	MPa	ASTM D638
Yield	60.0	MPa	ISO 527-2/50
Fracture ⁴	60.0	MPa	ASTM D638
Fracture	60.0	MPa	ISO 527-2/50

Tensile Elongation			
Yield ⁵	7.0	%	ASTM D638
Yield	10	%	ISO 527-2/50
Fracture ⁶	15	%	ASTM D638
Fracture	15	%	ISO 527-2/50
Flexural Modulus ⁷	2400	MPa	ISO 178
Flexural Stress	85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/2C
-30°C	4.0	kJ/m ²	ISO 179/2C
23°C	4.0	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength			ISO 179/2U
-30°C	80	kJ/m ²	ISO 179/2U
23°C	No Break		ISO 179/2U
Notched Izod Impact			
-30°C	36	J/m	ASTM D256
0°C	36	J/m	ASTM D256
23°C	38	J/m	ASTM D256
-30°C ⁸	4.0	kJ/m ²	ISO 180/1A
0°C ⁹	4.0	kJ/m ²	ISO 180/1A
23°C ¹⁰	4.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
-30°C	No Break		ASTM D4812
23°C	No Break		ASTM D4812, ISO 180/1U
-30°C ¹¹	100	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹²			
0.45 MPa, unannealed, 64.0mm span	150	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 64.0mm span	50.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	185	°C	ASTM D1525, ISO 306/B50, ISO 306/B120 ¹³
--	220	°C	ASTM D1525, ISO 306/A50 10 ¹⁴
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C, 1500 sec ⁻¹)	165	Pa · s	ISO 11443
Injection	Nominal Value	Unit	
Drying Temperature	110 - 120	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	40.0 - 60.0	°C	
Rear Temperature	230 - 245	°C	

Middle Temperature	240 - 255	°C
Front Temperature	245 - 265	°C
Nozzle Temperature	240 - 260	°C
Processing (Melt) Temp	250 - 270	°C
Mold Temperature	40.0 - 100	°C

NOTE		
1.	Tensile Bar	
2.	50 mm/min	
3.	Type 1, 50mm/min	
4.	Type 1, 50mm/min	
5.	Type 1, 50mm/min	
6.	Type 1, 50mm/min	
7.	2.0 mm/min	
8.	80*10*4	
9.	80*10*4	
10.	80*10*4	
11.	80*10*4	
12.	80*10*4 mm	
13.	标准 B (120°C/h), 载荷2 (50N)	
14.	速率 A (50°C/h), 载荷2 (50N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

