

Desmopan® DP 2786A

Thermoplastic Polyurethane Elastomer (Polyester)

Covestro - PUR

Message:

Coating grade; does not contain any anti-hydrolysis agent; Application; Textile coating

General Information			
Uses	Coating Applications		
	Fabric Coatings		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion Coating		
Physical	Nominal Value	Unit	Test Method
Density	1210	kg/m ³	ISO 1183 ¹
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	87		ISO 868 ²
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ³			DIN 53504
Break, 23°C	27.5	MPa	
10% Strain, 23°C	2.40	MPa	
50% Strain, 23°C	5.40	MPa	
100% Strain, 23°C	6.70	MPa	
300% Strain, 23°C	11.3	MPa	
Tensile Strain ⁴ (Break, 23°C)	600	%	DIN 53504
Abrasion Resistance (23°C)	46.0	mm ³	ISO 4649-A
Tensile Storage Modulus			ISO 6721-1,-4
-20°C	525	MPa	
20°C	40.0	MPa	
60°C	22.0	MPa	
Impact Resilience	43	%	ISO 4662
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ⁵	57	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	28	%	
70°C, 24 hr	61	%	
Injection	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Processing (Melt) Temp	190 to 210	°C	
Mold Temperature	20.0	°C	
Extrusion	Nominal Value	Unit	

Drying Temperature	< 80.0	°C
Melt Temperature	180 to 200	°C
NOTE		
1.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.	
2.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.	
3.	200 mm/min	
4.	200 mm/min	
5.	500 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

