

Vistek 3030

Thermoplastic
Visual Polymer Technologies, LLC

Message:

Vistek 3030 is a thermoplastic material. This product is available in North America.

The main features of Vistek 3030 are:

Good dimensional stability
Transparency

General Information			
Features		Good dimensional stability Definition, high	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	13	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	41.5	MPa	ASTM D638
Tensile Elongation (Break)	18	%	ASTM D638
Flexural Modulus	2170	MPa	ASTM D790
Flexural Strength (Yield)	57.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	89.4	°C	ASTM D648
Optical	Nominal Value	Unit	Test Method
Transmittance	90.0	%	ASTM D1003
Haze	4.3	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	193 - 232	°C	
Middle Temperature	193 - 232	°C	
Front Temperature	193 - 232	°C	
Mold Temperature	26.7 - 54.4	°C	
Injection instructions			

Pre-drying is typically not needed. In excessive humidity, pre-dry at 160° F for 2 to 4 hours.Back Pressure: Medium to High

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT