

ENFLEX S3150D

Thermoplastic Polyolefin Elastomer
ENPLAST Americas, a Ravago Group Company

Message:
50 Shore D TPE / TPO hybrid for injection molding applications. This grade offers flexibility, good resilience, and compatibility with Polypropylene.

General Information			
Features	Low compressive deformability		
	High elasticity		
	Solvent resistance		
	Good UV resistance		
	Recyclable materials		
	Workability, good		
	Good flexibility		
	Good coloring		
	Good adhesion		
	Ozone resistance		
	alkali resistance		
	Alcohol resistance		
	acid resistance		
	Detergent resistance		
	Oil resistance		
	Elastic		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw D, 10 seconds, extruded	46		ASTM D2240
Shore D, 10 seconds, injection molding	48		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	5.31	MPa	ASTM D412
Tensile Strength (Break)	14.5	MPa	ASTM D412
Tensile Elongation (Break)	650	%	ASTM D412
Tear Strength	71.8	kN/m	ASTM D624

Compression Set			ASTM D395B
23°C, 22 hr	65	%	ASTM D395B
70°C, 22 hr	79	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-50.0	°C	ASTM D746
Dynamic Service Temperature	90	°C	
Injection	Nominal Value	Unit	
Drying Temperature	65.6 - 71.1	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	171 - 199	°C	
Middle Temperature	177 - 210	°C	
Front Temperature	191 - 221	°C	
Nozzle Temperature	199 - 229	°C	
Processing (Melt) Temp	199 - 221	°C	
Mold Temperature	10.0 - 48.9	°C	
Injection Pressure	5.17 - 8.96	MPa	
Injection Rate	Fast		
Screw Speed	50 - 200	rpm	
Clamp Tonnage	2.8 - 4.8	kN/cm ²	
Cushion	5.08 - 12.7	mm	
Injection instructions			
Holding Time: 5 to 7 Sec.			
Extrusion	Nominal Value	Unit	
Drying Temperature	65.6 - 71.1	°C	
Drying Time	2.0 - 3.0	hr	
Hopper Temperature	160 - 177	°C	
Cylinder Zone 1 Temp.	171 - 191	°C	
Cylinder Zone 3 Temp.	179 - 199	°C	
Cylinder Zone 5 Temp.	191 - 210	°C	
Adapter Temperature	191 - 210	°C	
Melt Temperature	191 - 199	°C	
Die Temperature	191 - 210	°C	
Extrusion instructions			
Screw: L/D 20:1 or greater (L/D 24:1 preferred)Cooling Water: 60 - 85°F (15-30°C)Screw Speed: 100 - 200 rpmScreen Pack: 20/40/60			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

