

POLIMAXX 3342M

Polypropylene Random Copolymer
IRPC Public Company Limited

Message:

3342M is a Random Copolymer Polypropylene resin for injection molding and injection stretch blow molding process with high clarity characteristic. It is suitable for container, house-ware or any products that need clarity featuring. It also meets the F.D.A. requirement in the code of federal regulations in 21 CFR 177.1520 for food contact.

General Information	
UL YellowCard	E132283-100827228
Features	Food Contact Acceptable
	High Clarity
	Random Copolymer
Uses	Bottles
	Containers
	Crates
	Household Goods
Agency Ratings	FDA 21 CFR 177.1520
RoHS Compliance	RoHS Compliant
Processing Method	Injection Molding
	Injection Stretch Blow Molding

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	94		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.0	MPa	ASTM D638
Tensile Elongation (Yield)	37	%	ASTM D638
Flexural Modulus - 1% Secant	1080	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.5	kJ/m ²	DIN 53453
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	83.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

