

# Plaslube® ABS SL2

Acrylonitrile Butadiene Styrene

Techmer Engineered Solutions

Message:

Plaslube® ABS SL2 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in North America. Characteristics include:  
Flame Rated  
Lubricated

General Information			
Additive	Silicone Lubricant		
Features	General Purpose		
	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	4.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	31.7	MPa	ASTM D638
Tensile Elongation (Yield)	4.0	%	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Flexural Strength	63.4	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.14		
vs. Steel - Static	0.11		
Wear Factor	160	10 <sup>-8</sup> mm <sup>3</sup> /N · m	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C, 3.18 mm	53	J/m	
0°C, 3.18 mm	100	J/m	
23°C, 3.18 mm	270	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	104	°C	
1.8 MPa, Unannealed	77.8	°C	

Flammability	Nominal Value	Test Method
Flame Rating (1.50 mm)	HB	UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

