

Flexalloy® OR 9900-50

Polyvinyl Chloride Elastomer

Teknor Apex Company

Message:

Flexalloy® OR 9900-50 is a polyvinyl chloride elastomer (PVC elastomer) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is: extrusion.

Flexalloy® The main features of OR 9900-50 are:

- ROHS certification
- high molecular weight
- chemical resistance

Typical application areas include:

- Hose
- Wire and cable
- engineering/industrial accessories
- Tools
- Sealing applications

General Information			
Features	Ultra high molecular weight		
	Oil resistance		
Uses	Wire and cable applications		
	Washer		
	Power/other tools		
	Tools/Parts Box		
	Pipe		
	Pipe fittings		
	Seals		
	Footwear		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	9.10	MPa	ASTM D638
Tensile Elongation (Break)	390	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Compression Set (70°C, 22 hr)	35	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	90.0	°C	ASTM D794

Brittleness Temperature	-45.0	°C	ASTM D746
Additional Information			

膨胀,油浸,ASTM 3号油,125°C,7天:-0.5%动态热稳定性,205°C:50分钟

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

