

KumhoSunny PBT/ABS HBG5710

Acrylonitrile Butadiene Styrene + PBT

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HBG5710 is 10%GF reinforced PBT/ABS resin. HBG5710 has excellent mechanical strength, high chem-resistance and high shape resistance property. HBG5710 is mainly used in automobile parts, electric & electron parts, switch, office appliance,etc.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Chemical Resistance		
	Good Strength		
Uses	Appliances		
	Automotive Applications		
	Electrical Parts		
	Electrical/Electronic Applications		
	Switches		
UL File Number	E254819		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	30	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	80.0	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	4000	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	65	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	110	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	3.0 to 5.0	hr	

Processing (Melt) Temp	230 to 260	°C
Mold Temperature	50.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

