

Nylene® 406

Polyamide 6
Custom Resins Group

Message:

General purpose, fast cycling molding resin
Crystallization initiators provide fast molding cycles through rapid melt set-up
Parts molded from 406 have better dimensional stability at moisture equilibrium than parts molded from conventional nylon
Optimum processing conditions should provide a melt temperature of 450°F-470°F at the nozzle

General Information			
UL YellowCard	E40081-231513		
Features	Fast Molding Cycle		
	General Purpose		
	Good Dimensional Stability		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	75.2	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	25	%	ASTM D638
Flexural Modulus (23°C)	2760	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	43	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	182	°C	
1.8 MPa, Unannealed	71.1	°C	
Peak Melting Temperature	216	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating (1.47 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	232 to 243	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

