

TECOLITE KM-2000(G)

Phenolic

KYOCERA Chemical Corporation

Message:

Environmentally friendly and possible to substitution of metal parts. And High cost performance.
Kyocera Chemical's Phenolic molding compounds "TECOLITE" are environmentally friendly molding compounds. These acquired recognize UL94V-0 without any halogenated flame retardant.
These compounds have excellent properties in high temperature. Therefore, it is possible to use in high temperature environment for substitution metal parts and various electrical parts.

General Information			
Features	Environmentally Sound		
	High Heat Resistance		
Uses	Electrical/Electronic Applications		
	Metal Replacement		
Appearance	Black		
Physical	Nominal Value	Unit	
Specific Gravity	2.01	g/cm ³	
Molding Shrinkage - Flow ¹	0.20	%	
Mechanical	Nominal Value	Unit	
Flexural Modulus			
23°C	19000	MPa	
250°C	12500	MPa	
Flexural Strength			
23°C	160	MPa	
250°C	100	MPa	
Compressive Strength	225	MPa	
Thermal	Nominal Value	Unit	
Heat Deflection Temperature	> 300	°C	
Insulation Resistance			
After Boiling	1.0E+10	ohms	
As Molded	1.0E+11	ohms	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	> 10	kV/mm	
Arc Resistance	230	sec	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	V-0		UL 94
NOTE			
1.	Compression Molding		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

