Styropek® P 340H

Expanded Polystyrene

Styropek S.A. de C.V.

Message:

Styropek® P 40 products can be used in a wide variety of applications including protective packaging, food boxes, fish boxes, ice boxes and seedling trays.

Styropek® P 40 is an expandable polystyrene (EPS) in spherical beads which contains a min. of 4.4% and a max. of 5.8 %wt pentane as blowing agent. Do not contain chlorofluorocarbons and hydrochlorofluorocarbons compounds. Contains a maximum of 1000 ppm of residual monomer and 0.5% as maximum of total moisture.

All sizes present a bulk density of approximately 42 lb/ft³ (670 kg/m³).

Styropek® P 40 products are compatible with many anti-stat, mineral oils and colors additives added during the processing.

Intended uses

Shape molding applications, mid-range density with excellent fusion, regrind absorption and short cycle time.

| General Information | | |
|--------------------------------|---------------------------|-------|
| Additive | Blowing agent (4 to 6%) 2 | |
| Features | Recyclable materials | |
| | Can foam | |
| | | |
| Uses | Packaging | |
| | Foam | |
| | Container | |
| | | |
| Agency Ratings | EC 1907/2006 (REACH) | |
| | FDA 21 CFR 177.1640 | |
| | FDA 21 CFR 178.3010 | |
| | | |
| RoHS Compliance | RoHS compliance | |
| Forms | Sphere | |
| Physical | Nominal Value | Unit |
| Apparent Density | 0.67 | g/cm³ |
| Additional Information | Nominal Value | Unit |
| Bead Size (600.0 to 1180.0 µm) | > 97 | % |
| Expanded Density | 16.0 - 32.0 | kg/m³ |
| Monomer Residue | | ppm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

