

# HiFill® POM CO GF15 CC

Acetal (POM) Copolymer  
Techmer Engineered Solutions

Message:

HiFill® POM CO GF15 CC is an Acetal (POM) Copolymer product filled with 15% glass fiber. It can be processed by injection molding and is available in North America.  
Characteristics include:  
Flame Rated  
Chemically Coupled  
Copolymer

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	Chemically Coupled		
	Copolymer		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.90	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	82		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	103	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	4480	MPa	ASTM D790
Flexural Strength	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	154	°C	ASTM D648
CLTE - Flow	4.3E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	1.0	hr	
Rear Temperature	177 to 193	°C	

Middle Temperature	188 to 210	°C
Front Temperature	182 to 199	°C
Nozzle Temperature	177 to 204	°C
Processing (Melt) Temp	193 to 216	°C
Mold Temperature	82.2 to 121	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

