

Elastron® V V201.A40.N

Thermoplastic Vulcanizate

Elastron USA, Inc.

Message:

A soft, colorable thermoplastic vulcanizate, TPV (EPDM/PP) in the thermoplastic elastomer (TPE) family that offers higher temperature resistance and excellent compression set with superior UV resistance.

Bondable to: PP, EVA, PE

| General Information | | | |
|------------------------------|----------------------|-------|-------------|
| Features | Bondability | | |
| | Good Colorability | | |
| | Good UV Resistance | | |
| | High Heat Resistance | | |
| | Soft | | |
| RoHS Compliance | RoHS Compliant | | |
| Appearance | Natural Color | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.920 | g/cm³ | ASTM D792 |
| Molding Shrinkage | | | ASTM D955 |
| Flow | 3.2 | % | |
| Across Flow | 1.3 | % | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 40 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress | | | ASTM D412 |
| 100% Strain | 1.80 | MPa | |
| 300% Strain | 2.50 | MPa | |
| Tensile Strength (Break) | 3.20 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 550 | % | ASTM D412 |
| Tear Strength | 16.0 | kN/m | ASTM D624 |
| Compression Set | | | ASTM D395 |
| 23°C, 22 hr | 19 | % | |
| 70°C, 22 hr | 27 | % | |
| 100°C, 22 hr | 34 | % | |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | HB | | UL 94 |

| Additional Information | Nominal Value | Test Method |
|-----------------------------|---------------|-------------|
| Ozone Resistance - Stressed | No Cracks | ASTM D518 |

| Injection | Nominal Value | Unit |
|-----------------------|---------------|------|
| Drying Temperature | 90.0 | °C |
| Drying Time | 2.0 | hr |
| Suggested Max Regrind | 20 | % |
| Rear Temperature | 155 to 175 | °C |
| Middle Temperature | 165 to 185 | °C |
| Front Temperature | 170 to 190 | °C |
| Nozzle Temperature | 180 to 210 | °C |
| Mold Temperature | 25.0 to 50.0 | °C |

| Extrusion | Nominal Value | Unit |
|-----------------------|---------------|------|
| Drying Temperature | 90.0 | °C |
| Drying Time | 2.0 | hr |
| Cylinder Zone 1 Temp. | 155 to 165 | °C |
| Cylinder Zone 2 Temp. | 160 to 180 | °C |
| Cylinder Zone 3 Temp. | 165 to 185 | °C |
| Cylinder Zone 4 Temp. | 170 to 190 | °C |
| Cylinder Zone 5 Temp. | 180 to 210 | °C |
| Die Temperature | 185 to 215 | °C |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

