

SEETEC LLDPE UN324

Linear Low Density Polyethylene

Lotte Chemical Corporation

Message:

UN324 is manufactured by Unipol process technology.
UN324 has good mechanical properties and good processability.

General Information			
Additive	Antiblock		
	Antioxidant		
Features	Antiblocking		
	Antioxidant		
	Good Processability		
Uses	Film		
	Industrial Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.1	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	40	μm	ASTM D882
Tensile Strength			
MD : Break, 40 μm,Blown Film	43.1	MPa	
TD : Break, 40 μm,Blown Film	39.2	MPa	ASTM D882
Tensile Elongation			
MD : Break, 40 μm,Blown Film	730	%	
TD : Break, 40 μm,Blown Film	750	%	ASTM D1709
Dart Drop Impact (40 μm, Blown Film)	150	g	
Elmendorf Tear Strength ¹			
MD : 40.0 μm	49.0	kN/m	ASTM D1922
TD : 40.0 μm	98.1	kN/m	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 40.0 μm, Blown Film)	70		ASTM D2457
Haze (40.0 μm, Blown Film)	13	%	ASTM D1003
NOTE			
1.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

