

# ALCUDIA® LDPE 1970M

Low Density Polyethylene  
REPSOL

Message:

ALCUDIA® 1970M is a low density polyethylene grade of medium fluidity intended for those injection moulding applications in which good mechanical and good flow properties are required. Its formulation does not contain additives.

TYPICAL APPLICATIONS

Due to its good properties balance, ALCUDIA® 1970M is a very versatile grade and is suitable for articles of very diverse sizes:

Caps and closures.

Medium to large sized Industrial parts and components

Recommended melt temperature range from 180 to 230°C. Processing conditions should be optimised for each production line.

General Information			
Features	Additive Free		
	Food Contact Acceptable		
	Medium Flow		
Uses	Caps		
	Closures		
	Industrial Applications		
Agency Ratings	EU Food Contact, Unspecified Rating		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	47		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	9.00	MPa	ISO 527-2
Tensile Strain (Break)	120	%	ISO 527-2
Flexural Modulus	140	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	90.0	°C	ISO 306/A
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

