

CYCOLOY™ CY6414 resin

Polycarbonate + ABS

SABIC Innovative Plastics Europe

Message:

Flame retardant modified PC using non-brominated and non-chlorinated flame retardant systems, offering high heat for application in appliances, lighting and electrical market.

General Information			
UL YellowCard	E207780-101597016		
Features	Chlorine Free		
	Heat resistance, high		
	Bromine-free		
	Flame retardancy		
Uses	Lighting Applications		
	Electrical/Electronic Applications		
	Electrical appliances		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	14	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2330	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	64.0	MPa	ASTM D638
Fracture	62.0	MPa	ASTM D638
Tensile Elongation			
Yield ³	6.0	%	ASTM D638
Yield	5.7	%	ISO 527-2/50
Fracture ⁴	85	%	ASTM D638
Fracture	> 100	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵			ISO 179/1eA
-30°C	12	kJ/m ²	ISO 179/1eA
0°C	17	kJ/m ²	ISO 179/1eA
23°C	28	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	220	J/m	ASTM D256
0°C	530	J/m	ASTM D256

23°C	800	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	118	°C	ASTM D648
Vicat Softening Temperature			
--	134	°C	ISO 306/B50
--	135	°C	ISO 306/B120
Ball Pressure Test			IEC 60695-10-2
125°C ⁶	Pass		IEC 60695-10-2
125°C	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ISO 11359-2
Flow: -40 to 40°C	7.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	7.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	4.0E+16	ohms	IEC 60093
Dielectric Constant			ASTM D150
1 kHz	3.01		ASTM D150
1 MHz	2.95		ASTM D150
Dissipation Factor			
1 kHz	1.7E-3		ASTM D150
1 MHz	8.8E-3		ASTM D150, IEC 60250
Comparative Tracking Index (CTI)	PLC 3		UL 746
High Amp Arc Ignition (HAI)	PLC 1		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.20 mm	V-0		UL 94
2.50 mm	5VB		UL 94
Glow Wire Flammability Index ⁷ (0.750 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature ⁸			IEC 60695-2-13
0.750 mm	775	°C	IEC 60695-2-13
1.50 mm	775	°C	IEC 60695-2-13
3.00 mm	775	°C	IEC 60695-2-13
Oxygen Index	32	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 - 80.0	°C	
Rear Temperature	210 - 260	°C	
Middle Temperature	230 - 290	°C	
Front Temperature	240 - 300	°C	

Nozzle Temperature	230 - 290	°C
Processing (Melt) Temp	250 - 300	°C
Mold Temperature	60.0 - 90.0	°C

NOTE		
1.	5.0 mm/min	
2.	Type 1, 50mm/min	
3.	Type 1, 50mm/min	
4.	Type 1, 50mm/min	
5.	80*10*3 sp=62mm	
6.	by VDE	
7.	by VDE	
8.	by VDE	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT