

Next Nylon 66 Industrial Series PX-02NC

Polyamide 66

Next Polymers Ltd.

Message:

Description
PA66 UnFilled Natural Compound
Product Applications
Genral purpose application such as cable glands, fuse holder & panel board accessories and Textile parts etc
Benefits
Good dimension stability, Good strength & good creep resistance

General Information				
Features		Good Creep Resistance Good Dimensional Stability Good Strength		
Uses		Connectors Textile Applications		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS Compliant		
Appearance		Natural Color		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.14	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.75	--	%	
Across Flow	1.2	--	%	
Water Absorption				ASTM D570
23°C, 24 hr	2.1	--	%	
Saturation ¹	6.5	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
M-Scale	85	--		
R-Scale	120	--		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	75.0	55.0	MPa	ASTM D638
Tensile Elongation (Break)	30	> 50	%	ASTM D638
Flexural Modulus	3200	2400	MPa	ASTM D790
Flexural Strength	110	85.0	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method

Notched Izod Impact (23°C)	49	78	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	180	--	°C	
1.8 MPa, Unannealed	85.0	--	°C	
Melting Temperature	260	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+15	ohms·cm	IEC 60093
Electric Strength	22	--	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature - Hot Air Dryer	80.0		°C	
Drying Time	4.0 to 6.0		hr	
Suggested Max Moisture	0.20		%	
Rear Temperature	260 to 270		°C	
Middle Temperature	270 to 275		°C	
Front Temperature	275 to 280		°C	
Mold Temperature	65.0 to 85.0		°C	
NOTE				

1. Immersed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT