

# Propafilm™ RC120

Polypropylene Alloy

Innovia Films Ltd.

## Message:

Acrylic Coated Film

Biaxially oriented polypropylene (BOPP) film coated on both sides with an aqueous acrylic (chlorine free) dispersion.

RC100/120 are suitable for use as a direct product overwrap or carton overwrap in the bakery and confectionery industries, where aroma barrier and optimum product presentation are required.

General Information			
Features	Antiblocking		
	Flavor & Aroma Barrier		
	Food Contact Acceptable		
	Good Impact Resistance		
	Heat Sealable		
	Hot Tack Strength		
	Low Temperature Heat Sealability		
	Low Temperature Impact Resistance		
	Moisture Barrier		
	Opticals		
	Puncture Resistant		
Uses	Bags		
	Bi-axially Oriented Film		
	Food Service Applications		
	Laminates		
	Packaging		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage			Internal Method
Flow : 121°C, 1 min	2.0	%	
Flow : 129°C, 1 min	7.0	%	
Across Flow : 129°C, 1 min	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.25		
vs. Itself - Static	0.25		
Films	Nominal Value	Unit	Test Method
Seal Strength <sup>1</sup>	0.15	N/mm	Internal Method
Seal Initiation Temperature <sup>2</sup>	85.0 to 146	°C	Internal Method

Oxygen Permeability (25°C, 0% RH)	19	cm <sup>3</sup> ·mm/m <sup>2</sup> /atm/24 hr	ASTM F1927
Water Vapor Transmission Rate (38°C, 90% RH)	5.4	g/m <sup>2</sup> /24 hr	ASTM F1770
Film Gauge	120		Internal Method
Yield	36.6	m <sup>2</sup> /kg	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	95		ASTM D2457
Haze <sup>3</sup>	1.5	%	ASTM D1003
NOTE			
1.	265°F; 2secs; 15psi		
2.	2secs; 15psi		
3.	Wide angle; 2.5°		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

