

Latene® 9H TES/30

Polypropylene Homopolymer

LATI S.p.A.

Message:

Compound based on Polypropylene homopolymer (PPh).

Heat stabilised. Aesthetic talc. Product UL certified.

General Information			
UL YellowCard	E54080-244072		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Homopolymer		

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	1.2 to 1.5	%	
Flow : 2.00 mm	1.2 to 1.5	%	

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	2700	MPa	
60°C	1200	MPa	
90°C	650	MPa	
Tensile Stress			ISO 527-2/5
Yield, 23°C	25.0	MPa	
Yield, 60°C	15.0	MPa	
Yield, 90°C	10.0	MPa	
Break, 23°C	20.0	MPa	
Break, 60°C	10.0	MPa	
Tensile Strain			ISO 527-2/5
Yield, 23°C	4.0	%	
Yield, 60°C	5.0	%	
Yield, 90°C	6.0	%	
Break, 23°C	30	%	
Break, 60°C	70	%	

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	0.70	kJ/m ²	
23°C	2.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU

-20°C	15	kJ/m ²	
23°C	30	kJ/m ²	
Notched Izod Impact (23°C, 3.20 mm)	25	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	125	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	°C	ISO 75-2/A
Continuous Use Temperature ²	120	°C	
Vicat Softening Temperature	100	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	7.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	200 to 240	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Rate	Fast		
NOTE			
1.	at 60 Mpa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT