

ADEKA EH-5030S

Epoxy; Epoxide
Adeka Corporation

Message:
Low outgassing, rapid curing at low temperature

| General Information | | |
|----------------------------|----------------------|------|
| Features | Fast Cure | |
| | Low to No Outgassing | |
| Physical | Nominal Value | Unit |
| Chlorine Content | 0.1 | wt% |
| Particle Size - (d50) | 5.00 | µm |
| Active Hydrogen Equivalent | 105 g/eq | |
| Composition | 50 to 60 | % |
| Thermal | Nominal Value | Unit |
| Melting Temperature | 70.0 to 80.0 | °C |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT