

LG PS 25SP(E)

General Purpose Polystyrene

LG Chem Ltd.

Message:

LG PS 25SP(E) is a general-purpose polystyrene material. This product is available in North America, Latin America, Europe or Asia Pacific. The processing method is injection molding.

The main features of LG PS 25SP(E) are:

flame retardant/rated flame

Transparency

Typical application areas include:

Electrical/electronic applications

application of coating

General Information			
UL YellowCard	E67171-248672		
Features	Definition, high		
Uses	Electrical/Electronic Applications		
	Coating application		
Appearance	Clear/transparent		
Processing Method	Injection molding		
Multi-Point Data	Specific Heat vs. Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	3.0	g/10 min	ASTM D1238
220°C/10.0 kg	39	g/10 min	ASTM D1238
230°C/3.8 kg	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.80	%	ASTM D955

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	2880	MPa	ASTM D638
Tensile Strength ² (Yield, 3.20 mm)	52.0	MPa	ASTM D638
Tensile Elongation ³ (Break, 3.20 mm)	4.0	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	3270	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 3.20 mm)	98.1	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 6.40 mm	9.8	J/m	ASTM D256

23°C, 6.40 mm	9.8	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	95.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	88.0	°C	ASTM D648
Vicat Softening Temperature	96.0	°C	ASTM D1525 ⁶
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		UL 94
3.20 mm	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	170 - 190	°C	
Middle Temperature	180 - 200	°C	
Front Temperature	190 - 210	°C	
Nozzle Temperature	190 - 220	°C	
Processing (Melt) Temp	190 - 220	°C	
Mold Temperature	40.0 - 70.0	°C	
Back Pressure	29.4 - 58.8	MPa	
Screw Speed	30 - 60	rpm	
Injection instructions			
Minimum Moisture Content: 0.01%			
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	15 mm/min		
5.	15 mm/min		
6.	速率 A (50°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT